



Wasserflecken Water Marks



Ringförmige helle Flecken in der Lackoberfläche / Light circular marks on the finish

Ursachen:

- Verdunstung von Wassertropfen auf frisch lackierten und nicht ausgehärteten Lackierungen
- Wagenwäsche in praller Sonne

Vermeidung:

- Keine Wagenwäsche an frisch lackierten Fahrzeugen vornehmen
- Frisch lackierte Fahrzeuge nicht dem Regen aussetzen
- Lackoberfläche gut austrocknen lassen, bevor das Fahrzeug dem Kunden übergeben wird

Reparatur:

- Wasserflecken, die durch Wagenwäsche in praller Sonne entstanden sind, werden durch erneutes Waschen und Abledern, in hartnäckigen Fällen durch polieren, beseitigt.
- Vereinzelte, schwache Flecken, die durch Verdunstung von Wassertropfen auf nicht ausgehärteten Lackierungen entstanden sind, mit Schleifpapier der Körnung P1000 bis P1200 anschleifen und anschließend polieren.
- Je feiner das Schleifpapier, desto geringer ist die Beschädigung der Lackierung und somit der Polieraufwand.

Causes:

- Not allowing surface to cure properly before exposing it to the elements
- Washing the repaired area before it is sufficiently cured

Prevention:

- Avoid washing freshly repaired areas
- Do not give car to customer until repair is properly cured
- Do not expose freshly repair vehicle to precipitation or condensation

Repair

- Dry sand with P1200 or wet sand with P1500, limiting the area sanded
- Polish with 4CR 80 series polishes and 81 series pads