



Art.-No.:6.8020.1000

8020

Cutting Compound

Characteristics

Highly effective compound on aluminium oxide basis for the polishing of aged as well as for the treatment of fresh clearcoats suitably. Removes quickly use traces and overspray. Designed to eliminate grain 1500 – 2000 sanding scratches.

Tech Tip

Advantages:

- Dust formation through polishing minerals set free during polishing is limited
- Residues can be cleaned up easily after polishing
- Silicone free and safe for all paint shop applications

Application

1. Shake well before applying on a clean and properly cured surface. Avoid using in direct sunlight or on hot surfaces.
2. Use a soft foam polishing pad. Apply a 6'' line of polish over the surface with the pad to prevent slinging.
3. Polish at 1500-2000 rpm working slowly across a 2' x 2' section with medium pressure, overlapping each pass. Once the defects have been removed, reduce the pressure and continue polishing to a high gloss.
4. Clean the surface with a soft cloth immediately after polishing.

Removes 1500 – 2000 grit scratches.

Polishing machine: rotating 1500 – 2000 RpM

Type of coating:

Fresh coatings, regular

Aged/weathered coatings

Polishing pads:

Lambswool, Foam pad white (hard), Foam pad yellow (medium), Foam pad orange (soft)

Technical Data

pH-Value	7– 9
Colour	white
Viscosity	6 - 11 Pas
Density	1,46 kg/l

Storage and Transportation

At storage temperatures of preferably 15 to 25° C original packings may be stored for 24 months. Keep from freezing!